

SAXON KCP

DESCRIPTION

SAXON KENNEL & CATTERY PAINT is a solvent-based acrylic, it's a high-quality protective coating providing excellent durability, specifically formulated for use in dog kennels & catteries. It can be applied to concrete, blockwork, timber, fibre board and steel. It's resistant to mould growth and has excellent water abrasion resistance making it easy to clean. It may be applied all year round and becomes waterproof very rapidly.

Note the availability of water-resistant acrylic sealer paint for damp surfaces

COLOUR AND PRODUCT PRESENTATION

Colour range	See Saxon Colour Chart (other colours available on request)
Size	5 litre drum - 20 litre drum (larger sizes available on request)

MAIN PROPERTIES

PREPARED MIX PRODUCT	
Application	Roller, brush or spray gun/machine
Touch Dry	25 - 45 minutes depending on ambient temperature
Recoatable	16 - 24 hours, drying time will be significantly longer in cold and/or damp conditions.
Coverage	8 - 10 m ² per litre, this number could be lower on highly porous surfaces.
Thinning	Only for spray applications.
Cleaning	Clean equipment immediately after use with white spirit.
Colours	Black, Dark Brown, Sandstone, Grey, County Cream, Mid Brown
Shelf Life	18 months: if correctly stored to manufacturer's guidelines

LIMITATIONS

Do not apply if there are chances of rain, extreme air or substrate temperatures are below 8C or when the relative humidity is above 85% during application or drying period.

PREPARATION

New surfaces

All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Surfaces with suction (porous surfaces) should be treated with an application of previous coating recommended by the manufacturer based on surface conditions.



Previously painted surfaces

All surfaces must be sound, suitably dry and free from any contamination that will interfere with the adhesion of the materials to be applied. Remove all loose, failing or unsuitable material by scraping or brushing with a stiff bristle brush (do not use wire brush) to a sound edge. Dirt, fungus, rust or any other contaminant growth must be removed, and the areas treated before applying the coating. For surfaces in poor condition mechanical means may be necessary like pressure washing with a minimum 1500 psi, a proprietary paint removal system, wet or dry grit blasting. Care must be taken not to damage the underlying surface.

COATING SYSTEM APPLICATION

ROLLER



Stir well before and during use.

Apply using a roller, using it directly from the drum ensuring the entire sleeve is covered. Work in a methodical, systematic manner maintaining a manageable wet edge blending the material to achieve the desired pattern whilst still wet. Maintaining a continuous wet edge (approximately 1 m²)

BRUSH



Before use, flick the bristles back and forth to remove dust. Make sure you remove excess liquid before painting. Fill the brush by dipping in up to half the length of the bristles. Tap it gently against the side of the can: don't wipe the brush hard against the lip. The bristles should flex only slightly as you brush – don't over press – let the paint flow from the brush.

Start at the top and work down, painting with light even strokes, working back into the wet edge. If you are painting a large area by brush, apply paint to an area about 50cm x 50cm, then brush the paint in horizontal strokes to even the paint out and finish off with light vertical strokes all in one direction. If you are using a brush and roller, paint the edges of the area first.

SPRAY



For best results in terms of finish, coverage, speed of application and low overspray, the following set up is recommended.

Use conventional spray equipment i.e., GC 200/24 2HP compressor or larger, that can continuously deliver a minimum of 80psi at 4-5 cubic feet per minute



on a 3 meters (maximum) length airline to the spray gun. A GC 330 hopper feed spray gun with a 3mm air cap and tip size of 3-4mm tip size. Apply at 40psi air flow/spraying pressure with an 18" (450mm) distance from gun tip to surface being coated (target). Cover areas not to be sprayed with masking tape and wet strength masking paper or film. Spray using a circular or 'cross hatch' method, i.e. horizontally and vertically to achieve a full, uniform and even texture overall. Clean the tip and air cap frequently during use to prevent blocking.

Other painting methods and pumps can be used. Please contact Saxon Technical Support for further information.

SUBSTRATE TEMPERATURE

Substrate temperature during application and curing should be above 5°C (41°F)

Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

CLEANING

Return excess material/paint to container. Wash with clean water immediately after use.

HEALTH AND SAFETY RECOMMENDATIONS

Please refer to the Safety, Health and Environmental Information on the container. When preparing the surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask and recommended safety personal protection. Material Safety Data Sheets for this is available freely available at Saxon Coatings website.

STORAGE

Store in secure dry conditions. Keep out of reach of children. Containers should be kept closed during storage. Do not empty into drains, water rivers or access routes to septic drums.



GENERAL INFORMATION

Apply all products in accordance with BS 61 50: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by the manufacturer as it has no control over the conditions under which its products are applied.

For help or more information contact Saxon Coatings or visit our website at www.saxoncoatings.com Before using this product please ensure you have the latest information. The information is correct at date of issue February 2022.

WARRANTY

SAXON COATINGS warrant its title to the product, that the quality of the product conforms to Saxon Coatings' specifications for such product in effect at the time of manufacture and that the product shall be delivered free of the rightful claim of any third person for infringement of any patent covering the product. This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Saxon Coatings' technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. These are the only warranties that Saxon Coatings makes and all other express or implied warranties, under statute or arising otherwise in law, from a course of dealing or usage of trade, including without limitation, any other warranty of fitness for a particular purpose or use, are disclaimed by Saxon Coatings. Any claim under this warranty must be made by Buyer to Saxon Coatings in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify Saxon Coatings of such non-conformance as required herein shall bar Buyer from recovery under this warranty. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Saxon Coatings' representative for approval before commencing the work.

LIMITATIONS OF LIABILITY

The information in this document is given to the best of Saxon Coatings' knowledge. The information in this sheet is intended for guidance only and is based upon laboratory tests that Saxon Coatings' believes to be reliable. Saxon Coatings' products are considered as semi-finished goods and as such, products are often used under conditions beyond Saxon Coatings' control like the quality or condition of the substrate, or the many factors affecting the use and application of the product. The product and related information are designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Saxon Coatings' does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information. Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. Minor product variations may be implemented in order to comply with local requirements. Users should always consult Saxon Coatings' for specific guidance on the general suitability of this product for their needs and specific application practices. If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

